

The Mint of the United States,

AT

PHILADELPHIA, PENN.,

Assay Department,

July 5th, 1879

Mr. Gordon Snowden,

Dept. of

Sir,

The ingots cast at 10⁰⁰ A.M.
were rolled down to dollar thickness
without any annealing, and one
ingot was rolled to dime thickness
without annealing.

The metal improved $\frac{1}{4}$ thousandth
in fineness and lost but .35 of an oz.

I enclose a Memo of expenses

I am

Very Respectfully,

A. C. Underbrink

415 1/2

Essay Department
July 8/80

A. E. Outerbridge Jr

Edgmon Ingots
rolled to 60 lb and
dime this knife, without
annealing; improved
by the process.

Rec July 8/80

[Abstract:] Edgemoor Ingots rolled to dollar and dime thickness... 415 ½

The Mint of the United States,
At Philadelphia, Penn.,
Assay Department,
July 8, 1879

Hon. A. Loudon Snowden
Supt. &c.

Sir,

The ingots cast at Edge Moor were rolled down to dollar thickness without any annealing, and one ingot was rolled to dime thickness without annealing.

The metal improved $\frac{1}{4}$ thousandth in fineness and lost but .35 of an oz.

I enclose a memo. of expenses.

I am
Very Respectfully
A.E. Outerbridge Jr.